

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 24-000981
Issue Date : 8/04/2024
Print Date : 8/04/2024

Sample Description Clients Ref : "Clever 14mm Oak"
Engineered timber flooring
End Use : Flooring
Nominal Composition : Solid Oak Veneer with Multilayer Ply Core
Nominal Mass per Unit Area/Density : 750kg/m3
Nominal Thickness : 14mm



318687

69745

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 24-000981
Issue Date : 8/04/2024
Print Date : 8/04/2024

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 25-03-2024

Date Tested 08-04-2024

CHF Value	1	2	3	Mean
Length	5.8	-	-	- kW/m ²
Width	4.8	4.6	4.2	4.5 kW/m ²

HF-30 Value	1	2	3	Mean
Length	5.8	-	-	- kW/m ²
Width	4.8	5.0	5.0	4.9 kW/m ²

Smoke Value	1	2	3	Mean
Length	8	-	-	- % .min
Width	18	52	36	35 % .min

Blistering Yes

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

318687

69745

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR